

RYALUX CARPETS

Carpet Specification

William Twist

Carpet Type	- Twist
Method of Manufacture	- Broadloom Tufted
Gauge	- 1/8th
Pile Content	- 80% Wool (NZ) / 10% Nylon / 10% 'Wool-loc' Polyester
Yarn	- Singles
No. of Tufts (approx)	- 255,000 per sq mt 213,000 per sq yd
Pile Weight (above backing)	- 1,424 gms per sq mt 42 oz per sq yd
Total Weight (including backing)	- 2,530 gms per sq mt 75 oz per sq yd
Pile Height (above backing)	- 7 mm 1/4 (qtr) inch
Total Height (including backing)	- 10 mm 3/8th inch
Primary Backing	- Woven Polypropylene
Secondary Backing	- Hessian (Woven Jute) OR Woven Polypropylene
Insect Resistant (Mothproofing)	- Plain colours - No / Heather colours - Yes
Soil Protection Treatment	- Yes, Ryaguard
Static	- Low static at average relative humidity (not anti-static treated)
Flammability	- Low radius of flammability (BS 4790) / Class Dfl-s1 (BS EN 13501)
Tog Rating	- 1.1 (estimated value only)
Classification / Grade (recommended usage)	- Grade 5 Extra Heavy Domestic (Carpet Foundation SES) / Class 23 Heavy Domestic & Class 32 General Commercial (BS EN 1307)
Widths	- 4m & 5m
Colours	- 40 (32 Plain & 8 Heather)
Special Dye Option	- Not Available
Aftercare	- For Fitting, Cleaning & Maintenance advice, refer to our booklet 'Your Guide To Carpet Care'.

The above specifications are typical values only and are subject to normal manufacturing tolerance. Ryalux Carpets Ltd reserve the right to change or modify specifications (25/07/2012).

Ryalux Carpets Ltd, Mossfield Mill, Chesham Fold Road, Bury, Lancashire, BL9 6JZ.
Tel: 0845 652 8811, Fax: 0845 652 8822, e-mail: info@ryalux.com, web: www.ryalux.com