




MAYFAIR VELVET



▲ SB/DL: WCL.870



▲ SB/DL: WCL.850



▲ SB/DL: WCL.830




▲ SB/DL: WCL.805



▲ SB/DL: WCL.422



▲ SB/DL: WCL.289



▲ SB/DL: WCL.275



▲ SB/DL: WCL.295



▲ SB/DL: WCL.432



▲ SB/DL: WCL.230



▲ SB/DL: WCL.220



▲ SB/DL: WCL.482



▲ SB/DL: WCL.442



▲ SB/DL: WCL.250



▲ SB/DL: WCL.254



▲ SB/DL: WCL.212

MAYFAIR VELVET

lano carpets for hospitality

Fabricagemethode Technique de fabrication Manufacturing process Herstellungsverfahren Tecnica di fabbricazione	tufted, 1/10" saxony	Poolsamenstelling Nature du velours Pile composition Polmaterial Composizione pelo	WO	Tuftdoek Premier dossier Primary backing Trägermaterial Tela di supporto	woven	Rugtype Envers Secondary backing Rücken Fondo	SB/DL
Totale dikte Hauteur totale Total height Gesamthöhe Altezza totale	± 8,8 mm	Nuttige poolhoogte Hauteur de velours utile Effective pile height Tatsächliche Florhöhe Altezza pelo utile	± 6,8 mm	Breedte Largeur Width Breite Larghezza	± 400 & 500 cm	Aantal noppen/m ² Nombre de points/m ² Number of knots/sqm Noppenzahl/m ² Numero di punti/mq	± 200940
Poolinzetgewicht/m ² Poids mis en oeuvre/m ² Pile weight/sqm Poleinsatzgewicht/m ² Peso felpa/mq	± 1365 gr	Totaal gewicht/m ² Poids total/m ² Total weight/sqm Poleinsatzgewicht/m ² Peso totale/mq	± 2550 gr	EN 13501-1 Brandgedrag Comportement au feu Fire behaviour Brennverhalten Reazione al fuoco	B_{fl}-s1	EN 1307-2004 Classificatie Classification Classification Klassifizierung Classificazione	Class 23 Domestic Heavy Class 32 Commercial General
DIN 52612 Warmtedoorlaatweerstand Résistivité thermique Thermal retention Wärmedurchlaßwiderstand Resistenza termica	± 0,102 m²/kW	TOG rating	± 1,02	ISO 105 B02 2000 Lichtechtheid Solidité à la lumière Lightfastness Lichtechtheid Solidità colori alla luce	≥ 5-6	ISO 105 E01 2002 Waterechtheid verkleuring Solidité à l'eau changement couleur Waterfastness change in colour Wasserechtheit Änderung der Farbe Solidità colori all'acqua cambio colore	≥ 4
ISO 105 E01 2002 Waterechtheid uitbloeding Solidité à l'eau dégorgement Waterfastness staining Wasserechtheit anblüten Solidità colori all'acqua sfumatura colore	≥ 4	ISO 105 X12 2001 Wrijftechtheid droog Solidité au frottement sec Rubbingfastness dry Reibungechtheit trocken Solidità colori allo sfregamento a secco	≥ 4	ISO 105 X12 2001 Wrijftechtheid nat Solidité au frottement humide Rubbingfastness wet Reibungechtheit nass Solidità colori allo sfregamento a umido	≥ 4		

(±) These details are approximate. Complete specification details and associated certificates together with tolerances applying to the above can be provided upon request. We reserve the right to improve technical specifications without prior notice. Due to method of manufacture perfect pattern and/or colour matching cannot be guaranteed. The natural characteristics of woollen products result in shade variations & slight blemishes. They cannot be avoided without destroying the very nature of the product itself. In cut-pile carpeting, in rare cases, shading/pile reversal may occur without affecting its fitness for use. Shading/pile reversal can not be considered as a manufacturing or a material defect and will not affect the durability of the carpet.

For other languages see: www.lano.com



EN 14041



EN 1307

REG.NR
93221FDB

www.pro-dis.info



CARPETS TESTED FOR A BETTER LIVING ENVIRONMENT
















Lano
Zuidstraat 44
8530 Harelbeke-Belgium
t +32-56-65 40 00
f +32-56-65 40 09
marketing@lano.be
www.lano.com

The
**Green
signature**
of Lano Carpets

REACH
The new EU chemicals legislation