



Cloud 9 Cirrus

Cloud 9 APT

Excellent Thermal and Sound Reduction Properties

Excellent Recovery Characteristics

Now suitable for wood-block floors

Top Surface	Printed Stitch Bonded Crepe Paper	
Bottom Surface	White non-woven fabric	
Nominal Thickness	9.00 mm	
Nominal Roll Weight	15.0 Kg	33.1 lb
Weight Per Unit Area	995 g/m ²	29 oz/yd ²
Roll Length	11.0 m	36.0 ft
Roll Width	1.37 m	54 in
Guarantee	Lifetime of the Carpet (When used in recommended areas)	

BS. 5808 : 1991 Test Results - British Standard for Carpet Underlays

End Use Classification	BS. 5808	L/U
Work of Compression after 1000 impacts	BS. 4098	>150 J/m ²
Retention of Work of Compression	BS. 4098	>80 %
Loss in Thickness after Static Loading	BS. 4939	<5.00 %
Loss in Thickness after Dynamic Loading	BS. 4052	<5.00 %
Resistance to Cracking	BS. 5808 (A)	Pass

Other Relevant Tests

Thermal Resistance (TOG Rating)	BS. 4745	2.6 TOG Typical
Impact Sound Improvement Index (Test / Rated to BS EN ISO 140 - 8 / BS EN ISO 717-2)		39 dB
Hot Metal Nut Test	BS. 4790	Pass - Medium radius of effect

Disclaimer

Whilst every effort is made to ensure its accuracy, the data on this sheet is meant for information purposes only. The typical properties listed are the result of extensive laboratory tests, but since Ball and Young has no control over the end use of each material, we cannot guarantee these results are obtained in practice. Users should conduct their own tests to determine the suitability of each material to its intended application.

CLOUD



RANGE OF UNDERLAYS

PURE LUXURY UNDER THE CARPET

Recommended Areas of Use

Suitable for luxury use areas.

Living rooms and bedrooms.

Luxury domestic use.

CLOUD

