

## Underlay Technical Specification

Item Code: TAK080013

Issue Date: 18/4/2013

Issue No. 8



### Sponge Rubber

**Suitable for underfloor heating**

**Suitable for the stretch-fit installation of carpets**

**End Use Classification (BS 5808: 1991): L/U, Luxury Use**

#### Standard Specifications

Nominal square weight †	4238 g/m <sup>2</sup> (125 oz/yd <sup>2</sup> )
Nominal roll weight†	46.6 kg (102 lb)
Roll area*	10.96m <sup>2</sup> (1.33m x 8.24m)

#### BS 5808: 1991

End Use Classification	L/U, Luxury Use	
Nominal thickness <sup>†</sup>	8.30mm	BS 4051
Work of compression Minimum 50 J/m <sup>2</sup>	150 J/m <sup>2</sup>	BS 4908 & BS 4052
Retention of work of compression (min 40%)	98 %	BS 4908 & BS 4052
Compression after dynamic loading	4.6 mm	BS 4908 & BS 4052
Loss in thickness after dynamic loading (max 15%)	2.5%	BS 4052
Loss in thickness after static loading (max 15%)	3.0 %	BS 3939
Breaking strength (length/width) min. 40N	182N / 126N	BS 2576
Extension under force (length/width) max. 10% @ 40N	2.2 % / 1.0 %	BS 2576
Resistance to cracking (not greater than 50mm)	Pass	BS 5808

#### Flammability

Hot metal nut test (tested in Interfloor laboratory)	Low radius of effects of ignition	BS 4790 & BS 5287
--	-----------------------------------	-------------------

#### Other Specifications

Odour	No objectionable odour	
Antimicrobial and mildew resistant	Yes	
Colour / backing	Black / unprinted Textron® backing	
Packaging	Cream film / blue print	
Thermal resistance	0.80 togs	BS 4745
Impact sound reduction (Delta Lw)	42 <sup>‡</sup>	BSEN ISO 140-8: 1998 and BSEN ISO 717-2: 1997
Emissions (US Carpet & Rug Institute)	Meets low VOC emission criteria	

#### Certification



#### Guarantee

Guaranteed for the serviceable lifetime of the carpet when used in accordance with the End Use Classification.

#### Notes

\* The nominal roll dimensions have been quoted. These may vary slightly, but will still equate to the area quoted. This does not constitute a manufacturing specification. It details important performance and physical characteristics only.

† ±5%

‡ Value derived from similar product test results