

## Victoria Twist (50oz)

Range	Solid	Heather
Suitability Domestic Suitability EN1307	Extra Heavy 33	Extra Heavy 33
Comfort Factor	5	5
Construction	Tufted Twist	Tufted Twist
Pile Fibre Content	80% Wool, 20% Polypropylene	80% Wool, 20% Polypropylene
Machine Gauge	39.37/10cm (1/10th)	31.5/10cm (1/8th)
Stitch Rate	46.3/10 cm (11.75 S.P.I)	45.3/10 cm (11.5 S.P.I)
Pile Weight	1695gms/m <sup>2</sup> (50oz/yd <sup>2</sup> )	1695gms/m <sup>2</sup> (50oz/yd <sup>2</sup> )
Total Carpet Weight	2245gms/m <sup>2</sup> (66.21oz/yd <sup>2</sup> )	2245gms/m <sup>2</sup> (66.21oz/yd <sup>2</sup> )
Pattern Repeat	N/A	N/A
Tuft Density	182,243/m <sup>2</sup> (117.5/in <sup>2</sup> )	143,230/m <sup>2</sup> (92.4/in <sup>2</sup> )
Pile Height	8mm (0.315")	8mm (0.315")
Total Thickness	10mm (0.394")	10mm (0.394")
Tog Rating	1.25	1.25
Primary Backing	Woven Polypropylene	Woven Polypropylene
Secondary Backing	LOC - weave®	LOC - weave®
Widths Available	4m (13'1") & 5m (16'5")	4m (13'1") & 5m (16'5")
Abrasion Resistance	In excess of 40,000 rubs	In excess of 30,000 rubs
Static Loading	88%	82%
CE Mark	EN14041: 2004 CLASS:Dfl-s1 SLIP: NPD	EN14041: 2004 CLASS:Dfl-s1 SLIP: NPD
Flammability Test Data	Low Radius Effects of Ignition	Low Radius Effects of Ignition
Light Fastness	5	5
Shampoo Fastness	4	4

This specification is correct at date of issue and details provided are accurate within expected tolerances.  
Victoria Carpets Ltd. reserve the right to amend this specification without prior notice.