

Victoria Twist (60oz)

Range	Solid	Heather
Suitability Domestic Suitability EN1307	Extra Heavy 33	Extra Heavy 33
Comfort Factor	5	5
Construction	Tufted Twist	Tufted Twist
Pile Fibre Content	80% Wool, 20% Polypropylene	80% Wool, 20% Polypropylene
Machine Gauge	39.37/10cm (1/10th)	31.5/10cm (1/8th)
Stitch Rate	48.4/10cm (12.30 S.P.I)	47.6/10cm (12.10 S.P.I)
Pile Weight	2035gms/m ² (60oz/yd ²)	2035gms/m ² (60oz/yd ²)
Total Carpet Weight	2595gms/m ² (76.53oz/yd ²)	2560gms/m ² (75.50oz/yd ²)
Pattern Repeat	N/A	N/A
Tuft Density	190,669/m ² (123/in ²)	150,200/m ² (96.8/in ²)
Pile Height	9.5mm (0.374")	9.5mm (0.374")
Total Thickness	11.5mm (0.453")	12.1mm (0.476")
Tog Rating	1.5	1.5
Primary Backing	Woven Polypropylene	Woven Polypropylene
Secondary Backing	LOC - weave®	LOC - weave®
Widths Available	4m (13'1") & 5m (16'5")	4m (13'1") & 5m (16'5")
Abrasion Resistance	In excess of 45,000 rubs	In excess of 37,000 rubs
Static Loading	88%	85%
CE Mark	EN14041:2004 CLASS:Dfl-s1 SLIP: NPD	EN14041:2004 CLASS:Dfl-s1 SLIP: NPD
Flammability Test Data	Low Radius Effects of Ignition	Low Radius Effects of Ignition
Light Fastness	5	5
Shampoo Fastness	4	4

This specification is correct at date of issue and details provided are accurate within expected tolerances.
Victoria Carpets Ltd. reserve the right to amend this specification without prior notice.