



SONEVA



version
replaces

17/03/2020
14/02/2020

Manufacturing type	Herstellungsart	Mode fabrication	Productie methode	tufted 1/10"	
Construction	Struktur	Structure	Structuur	2-ply saxony	
Pile composition	Polmaterial	Couche d'usure	Poolsamenstelling	100% PA - Econyl®	
Dye method	Farbgestaltung	Coloration	Kleurverwerking	solution dyed	
Primary backing	Trägermaterial	Premier dossier	Tuftdoek	woven	
Secondary backing	Rückenausrüstung	Dossier	Rug	action backing	
Pile weight	Poleinsatzgewicht	Poids de velour	Poolgewicht	ISO 2424	g/m2 1.600 (+/-)
Total weight	Gesamtgewicht	Poids total	Totaal gewicht	ISO 8543	g/m2 2.400 (+/-)
Pile height	Polhöhe	Hauteur du velours	Poolhoogte	ISO 1766	mm 8,5 (+/-)
Total height	Gesamtdicke	Epaisseur totale	Totale dikte	ISO 1765	mm 10,0 (+/-)
Tuft density	Noppenzahl	Nombre de touffes	Aantal punten	ISO 1763	/m2 220.000 (+/-)
Width	Breite	Largeur	Breedte		cm 400 - 500
Classification	Klassifikation	Classement	Gebruiksklasse	EN 1307	33 heavy commercial
Comfort rating	Komfortklasse	Classement confort	Comfort klasse	EN 1307	LC 5
Castor chair	Stuhllroleneignung	Chaise à roulettes	Rolstoelgeschikt	EN 985	A intensive
Stair suitability	Treppeneignung	Escaliers	Trappengeschikt	EN 1963	B occasional
Fire resistance	Brennverhalten	Comportement feu	Brandgedrag	EN 13501-1	Cfl-s1 glued
Permanent antistatic	Permanent Antistatisch	Antistatique permanent	Permanent antistatisch	ISO 6356	kV ≤ 2,0
Transversal resistance	Durchgangswiderstand	Résistance transversale	Doorgangsweerstand	ISO 10965	Ω ≤ 10 ⁹
Thermal resistance	Wärmedurchlaßwiderstand	Résistance thermique	Warmteoorlaatweerstand	ISO 8302	m2/K/W 0,114 TOG 1,14
Sound absorption	Schallabsorptionsgrad	Absorption phonique	Geluidsabsorptie	ISO 354	α _w 0,25
Impact sound reduction	Trittschallverbesserungsmaß	Isolation phonique	Geluidsisolatie	ISO 10140	ΔL _w 30 dB
			ISO 10140	ΔL	46 dB (1000 Hz)
Colour fastness light	Lichtechtheit	Solidité à la lumière	Lichtechtheid	ISO 105 B02	7-8
Rubbing fastness	Reibechtheit	Solidité au frottement	Wrijftechtheid	ISO 105 X12	≥ 5



 20 EN 14041 DOP 000620A-001	
	
	
	
TAPIBEL NV Industrielaan 4 B-3900 Pelt Belgium +32 11 80 48 50 sales@tapibel.be www.tapibel.be	
EN 1307 for use as floorcovering in buildings (EN 14041) according to the manufacturer's specification	



TÜV Emission testing

Results comply with emission threshold of

- AgBB - Germany
- Belgian VOC regulation
- BREEAM Exemplary level
- French VOC regulation
- LEED V4 (outside North America)



MAINTENANCE - INSTALLATION

visit our website www.tapibel.be or contact
the sales desk for more detailed information

Made with 100% Regenerated Nylon



These technical details are approximate. Complete specification details and associated certificates together with tolerances applying to the above can be provided upon request, if available. We reserve the right to alter specifications without notice. Due to the method of manufacture, perfect pattern/colour matching cannot be guaranteed.

Shading/pile reversal might occur in cut pile carpets, without affecting overall quality and suitability. It is not considered as a manufacturing fault.

Tapibel

SONEVA

New
Worlds
splend



620-10 POLAR BEAR



620-11 BORA BORA



620-20 WALVIS BAY



620-22 GOBI DESERT



620-24 WYOMING



620-40 OYSTER



620-41 NORDIC STONE



620-42 LEMUR



620-43 PATAGONIA



620-44 KOALA



620-47 MISTY FJORD

SDN
solution dyed nylon
bleach cleanable yarn

Made with 100% Regenerated Nylon

ECONYL®