



CLOUD 9 NIMBUS

- CLOUD 9 APT
- SUITABLE FOR GENERAL DOMESTIC AND LUXURY USE
- EXCELLENT RECOVERY CHARACTERISTICS
- EASY TO LIFT AND HANDLE

RECOMMENDED AREAS OF USE

SUITABLE FOR LUXURY USE AS WELL AS GENERAL DOMESTIC AREAS SUCH AS LIVING ROOMS AND BEDROOMS. SUITABLE FOR WOOD BLOCK FLOORS.

STANDARD SPECIFICATIONS

TOP SURFACE	Printed stitch bonded crepe paper	
BOTTOM SURFACE	White non-woven fabric	
NOMINAL THICKNESS	7.00 mm	
NOMINAL ROLL WEIGHT	12.0 kg	26.4 lb
WEIGHT PER UNIT AREA	796 g/m ²	23 oz/yd ²
ROLL LENGTH	11.0 m	36.0 ft
ROLL WIDTH	1.37 m	54 in
GUARANTEE	Lifetime of the initial carpet installation (when used in recommended areas)	

BS. 5808 : 1991 TEST RESULTS - BRITISH STANDARD FOR CARPET UNDERLAYS

END USE CLASSIFICATION	BS.5808	L/U or GD/U
WORK OF COMPRESSION AFTER 1000 IMPACTS	BS.4098	>110 J/m ²
RETENTION OF WORK OF COMPRESSION	BS.4098	>80 %
LOSS IN THICKNESS AFTER STATIC LOADING	BS.4939	<5.00 %
LOSS IN THICKNESS AFTER DYNAMIC LOADING	BS.4052	<5.00 %
RESISTANCE TO CRACKING	BS.5808 (A)	Pass

OTHER RELEVANT TESTS

THERMAL RESISTANCE (TOG RATING)	BS.4745	1.9 TOG
IMPACT SOUND IMPROVEMENT INDEX (Test/Rated to BS EN ISO 140-8 / BS EN ISO 717-2)		34 dB
HOT METAL NUT TEST	BS.4790	Pass - Low radius of effect

ISSUE 4 02-MAY-08

DISCLAIMER

Whilst every effort is made to ensure its accuracy, the data on this sheet is meant for information purposes only. The typical properties listed are the result of extensive laboratory tests, but since Ball & Young has no control over the end use of each material, we cannot guarantee these results are obtained in practice. Users should conduct their own tests to determine the suitability of each material to its intended application.


Ball & Young Ltd
 A Vita Group Company